


## Heavy-Duty PE Tape



<b>Backing:</b>	Polyethylene Film
<b>Adhesive:</b>	Synthetic Rubber
<b>Liner:</b>	N/A
<b>Colors:</b>	Red, White, Clear
<b>Specifications:</b>	N/A
<b>Standard Sizes:</b>	48mm x 55m, 96mm x 55m

### Applications

- Temporary enclosures and containment areas for remediation and marine applications
- Heavy-duty bundling, wrapping, and repairs
- Bonding to low surface energy materials
- Temporary surface and floor protection
- Heavy-duty polyethylene splicing and hanging
- Seam and patch shrink wrap for indoor/outdoor storage of marine, RV, and other equipment
- Dissimilar metal separation
- Waterproof packaging

### Features

- Polyethylene Film Backing
- Synthetic Rubber Adhesive

### Benefits

- Thick facer for added strength durability
- Conformable and flexible
- Low elongation for constant surface bond
- Pinked/Serrated edge available for hand tearability
- Formulated to adhere to low surface energy materials such as PE films
- High tack for good quick stick
- Superior bond to rough or challenging surfaces
- Excellent shear strength
- Repositionable and clean removal from many surfaces
- Environmentally friendly and safe to use
- Low VOC, Contains no heavy metals (such as lead and chromium)

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness (Colors)</b>	9.0 mils	0.229 mm	ASTM D-1000
<b>Adhesion to Steel</b>	85 oz/in	9.30 N/cm	PSTC-101
<b>Adhesion to Backing</b>	40 oz/in	4.38 N/cm	PSTC-101
<b>Tensile Strength</b>	30 lb/in	52.54 N/cm	ASTM D-1000
<b>Permeance</b>	0.10 US Perms		ASTM D-3833
<b>Application Temperature</b>	30 to 160 °F	-1 to 71 °C	
<b>Operating Temperature</b>	20 to 200 °F	-7 to 93 °C	
<b>Elongation</b>	65%		

Recommended Storage Conditions: 60-80 °F at 40-60% RH

Standard Shelf Life (at 25 °C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.