

627-35

Shadowlastic[™] Plus - Roof Flashing Tape

Liner Adhesive Backing	Backing:	Woven Polyethylene (Printed)		
	Adhesive:	Butyl Rubber		
	Liner:	Kraft Paper Liner		
	Colors:	Black (w/White Print)		
	Specifications	AAMA-711, ASTM E2112		
	Standard Sizes	6 "x50Ft, 9"x50Ft		
	Applicati	ons		
• Flashing hip, ridge, and penetration deta		Deck-to-wall joints		
on concrete tile roofs		Sheet metal repairs on mobile homes, trailers		
 Sealing gutters, roof valleys and eaves, 		Sealing other detail areas against water and		
chimneys and vents, and rooftop duct systems		air penetration		
chilling's and vents, and toortop duct sy	sterns			
Features		Benefits		
Woven Polyethylen Backing	•	Conformable and durable		
, , , ,	•	Excellent air and moisture barrier properties		
	•	Suitable for up to 3 years outdoor UV exposure		
Butyl Rubber Adhesive	•	Provides permanent weather-tight seal on		
····, ·····		most clean, dry building surfaces		
	•	Excellent all-temperature performance		
	•	Compatible with sealants & caulking		
	•	Self-healing after puncture		
Kraft Paper Liner		Easy to use		
	•	Lasy to use		

Physical Properties

		•		
	Standard UOM	Metric UOM	Test Method	
Total Thickness	35 mils	889 mic	ASTM D-1000	
Adhesion to Steel	229 oz/in	25.06 N/cm	ASTM D903-93	
Adhesion to Plywood	251 oz/in	27.47 N/cm	ASTM D903-93	
Adhesion to OSB	232 oz/in	25.39 N/cm	ASTM D903-93	
Adhesion to PVC	241 oz/in	26.38 N/cm	ASTM D903-93	
Adhesion to Cement Brick	246 oz.in	26.93 N/cm	ASTM D903-93	
Tensile Strength	59 lb/in	103.33 N/cm	ASTM D412-97	
Installation Temperature	30 to 180° F	-1 to 82° C		
Operating Temperature	-30 to 200° F	-34 to 93° C		

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility intended user.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryplastics.com