

# Stretch-Vac® Pro-Rap

## Vacuum bagging film

Ideally suited to low temperature applications

### Features

- Copolymer medium temperature film which can be used for cures up to 121°C (250°F) whilst remaining soft and pliable.
- Engineered for use with most commonly used resin systems including phenolics.
- Can be heat sealed to meet any customer shape requirements.
- Not affected by environmental humidity levels in the storage or work place.

### Properties

Maximum use temperature	121°C	250°F
Colour	Blue	
Tensile strength at break (ASTM D882)	34MPa	5000PSI
Elongation at break (ASTM D882)	650%	
Yield	18.5m <sup>2</sup> /kg	90.4 ft <sup>2</sup> /lb

### Availability

Thickness	69µm	0.0027in
Roll weight	Up to 30kg	Up to 66lbs
Widths	Up to 1.52m (open)	Up to 60in (open)
Formats available	V sheet and sheet	

### Storage

Do not store rolls vertically on their ends.

### Health & safety

Handling of these products must conform to individual company guidelines and health and safety regulations.

All statements, technical information and recommendations contained in this data sheet are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any subsequent contract. All products are sold subject to the Cytec's Standard Terms and conditions of Sale. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. It is the responsibility of those wishing to sell items made from or embodying the products to inform the user of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information contained herein is under constant review and liable to be modified from time to time.  
© Copyright 2012 – Cytec Process Materials (Keighley) Ltd, Cytec Process Materials (CA) Inc, Cytec Process Materials (Toulouse) Sarl, Cytec Process Materials (Milan) Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.