

tesa® 4963

Double-sided transparent film tape

PRODUCT INFORMATION

Product Description

tesa® 4963 is a transparent double-sided self-adhesive tape consisting of a PVC-carrier and a rubber adhesive mass system. tesa® 4963 is largely resistant to plasticizers.

tesa® 4963 is also available in spools with an extended liner acting as "fingerlift," enabling easy liner removal.

Main Application

- permanent closure for paper and plastic bags
- self-adhesive mounting of decorative and packaging materials
- splicing of paper, plastic films and metal foils
- fixing of promotion material

Technical Data

- Backing material PVC film Type of adhesive natural rubber
- Color
 transparent
 Elongation at break
 30 %

 Total thickness
 110 µm
 Tensile strength
 50 N/cm

4.3 mils

Adhesion to

- Steel (initial) 5.9 N/cm Steel (after 14 days) 6.1 N/cm 53.9 oz/in 55.7 oz/in
- ABS (initial) 5.4 N/cm ABS (after 14 days) 6.2 N/cm 49.3 oz/in 56.6 oz/in
- Aluminium (initial)

 4.0 N/cm
 36.5 oz/in

 aluminium (after 14 days)
 4.7 N/cm
 42.9 oz/in
 42.9 oz/in
 - PC (initial) 6.2 N/cm PC (after 14 days) 6.6 N/cm 56.6 oz/in 60.3 oz/in
 - PE (initial) 3.8 N/cm PE (after 14 days) 4.5 N/cm 34.7 oz/in 41.1 oz/in
 - PET (initial) 5.2 N/cm PET (after 14 days) 5.4 N/cm 47.5 oz/in 49.3 oz/in
 - PP (initial) 4.3 N/cm PP (after 14 days) 4.6 N/cm 39.3 oz/in 42 oz/in
- PS (initial) 5.3 N/cm PS (after 14 days) 6.6 N/cm 48.4 oz/in 60.3 oz/in
- PVC (initial) 5.0 N/cm PVC (after 14 days) 5.9 N/cm 45.7 oz/in 53.9 oz/in

For latest information on this product please visit http://l.tesa.com/?ip=04963

Page 1 of 2 / As of 11/01/14

28.6 lbs/in

tesa tape, inc.

Technical Tape México S.A. de C.V.

5825 Carnegie Boulevard Charlotte, NC 28209 Phone: 704 554 0707 Toll Free: 800 426 2181 Fax: 800 852 8831 customercare@tesatape.com Av. Santa Fe No. 170 German Centre P 6-3-3Col. Lomas de Santa Fe Mexico D.F. C.P. 01210 Phone: +52 (55) 5292 6978 Fax: +52 (55) 5292 6977

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to advise you.



0

Properties

Tack

Temperature resistance short term 70 °C

158 °F

Resistance to chemicals Softener resistance

Static shear resistance at 73,4 °F ++

Static shear resistance at 104 °F

++ Evaluation across relevant tesa® assortment: ++ very good, + good, o medium, - low

Additional Info

tesa® 4963 is also available with fingerlift (extended liner) for easy removal of liner.

Liner variants:

• PV0 brown creped PVC film

Ageing resistance (UV)

Humidity resistance

PV1 brown glassine paper (71?m)

For latest information on this product please visit http://l.tesa.com/?ip=04963

Page 2 of 2 / As of 11/01/14

tesa tape, inc.

5825 Carnegie Boulevard Charlotte, NC 28209 Phone: 704 554 0707 Toll Free: 800 426 2181 Fax: 800 852 8831 customercare@tesatape.com

Technical Tape México S.A. de C.V.

Av. Santa Fe No. 170 German Centre P 6-3-3Col. Lomas de Santa Fe Mexico D.F. C.P. 01210 Phone: +52 (55) 5292 6978 Fax: +52 (55) 5292 6977

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to advise you.