

Vac-Pak® HS 8171 6/66

Vacuum bagging film

Ideally suited to high temperature and pressure applications

Features

- Heat stabilised, co-extruded co-polymer film produced from modified nylon resin.
- High temperature film which can be used for cures up to 204°C (400°F) and remains pliable after extended cure cycles.
- The co-extrusion process combines multiple layers of resin flow into film prior to exiting the extrusion die. This process represents the most advanced state of the art technology in blown film production.
- Ideal for advanced composite fabrication and other high temperature/pressure applications when softness and workability are essential.
- Can be heat seamed to meet any customer shape requirements.

Properties

| Maximum use temperature | 204°C | 400°F |
|---------------------------------------|--|---|
| Colour | Clear, blue and green | |
| Tensile strength at break (ASTM D882) | 103MPa | 15000PSI |
| Elongation at break (ASTM D882) | | 400% |
| Yield | 50µm: 17.30m ² /kg 75µm: 11.60m ² /kg | 9.39yd ² /lb 6.3yd ² /lb |

Availability

| | | |
|-------------------|-------------------------------|--------------------|
| Thickness | 50 and 75µm | 0.002 and 0.003in |
| Roll weight | Up to 45kg | Up to 100lbs |
| Widths | Up to 4m (open) | Up to 160in (open) |
| Formats available | V sheet, sheet, lay flat tube | |

Storage

Do not store rolls vertically on their ends.

Health & safety

Handling of these products must conform to individual company guidelines and health and safety regulations.

All statements, technical information and recommendations contained in this data sheet are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any subsequent contract. All products are sold subject to the Cytec's Standard Terms and conditions of Sale. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. It is the responsibility of those wishing to sell items made from or embodying the products to inform the user of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information contained herein is under constant review and liable to be modified from time to time.

© Copyright 2012 – Cytec Process Materials (Keighley) Ltd, Cytec Process Materials (CA) Inc, Cytec Process Materials (Toulouse) Sarl, Cytec Process Materials (Milan) Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.