

# Vac-Pak® E3760

## Release film

Ideally suited to mild contour and flat panel applications

### Features

- Excellent for mild contour and flat parts as it will lie flat and smooth, with little wrinkling issues, as experienced with other, more pliable, release films.
- Available perforated or non-perforated.

### Properties

Maximum use temperature	204°C	400°F
Colour	Clear and white	
Film	PVF	
Standard perforation patterns	Contact us for full details	
Tensile strength at break	69MPa	10,000psi
Elongation (at break)	200%	
Yield	28.6m <sup>2</sup> /kg	140ft <sup>2</sup> /lb/mil

### Availability

Thicknesses	25 and 50µm	0.001 and 0.002in
Standard widths	Up to 3m	Up to 118in
Standard length	Up to 914m	Up to 3000ft

### Storage

Store in original packaging

### Health & safety

Handling of these products must conform to individual company guidelines and health and safety regulations.

All statements, technical information and recommendations contained in this data sheet are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any subsequent contract. All products are sold subject to the Cytec's Standard Terms and conditions of Sale. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. It is the responsibility of those wishing to sell items made from or embodying the products to inform the user of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information contained herein is under constant review and liable to be modified from time to time.  
© Copyright 2012 – Cytec Process Materials (Keighley) Ltd, Cytec Process Materials (CA) Inc, Cytec Process Materials (Toulouse) Sarl, Cytec Process Materials (Milan) Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.