


36H

Double-Coated Mounting Tape



	Standard UOM	Metric UOM		Test Method		
Carrier Thickness	0.5 mils	ils 13 mic		PSTC-133		
Adhesive Thickness (Air Side)	1.9 mils	48 mic		PSTC-133		
Adhesive Thickness (Liner Side)	1.9 mils	48 mic		PSTC-133		
Adhesion to Steel (Air Side)	88 oz/in	959 N/m		PSTC-101		
Adhesion to Steel (Liner Side)	93 oz/in	1014 N/m		ASTM D-1000		
Shear Strength	>24 hours			PSTC-107		
Application Temperature Range	50 to 150° F	10 to 65° C				
Maximum Continuous Use Temp	200° F	93° C				
Maximum Intermittent Temp	250° F	121° C				
Adhesion to Common Substrates:	ABS	44 oz/in	4.82 N/cm	PET	54 oz/in	5.91 N/cm
	Acrylic	47 oz/in	5.14 N/cm	Polystyrene	38 oz/in	4.16 N/cm
	HDPE	18 oz/in	1.97 N/cm	PP	16 oz/in	1.75 N/cm
	LDPE	25 oz.in	2.74 N/cm	PVC	55 oz/in	6.02 N/cm
	Nylon	43 oz/in	4.71 N/cm	TPO	17 oz/in	1.86 N/cm
	PC	56 oz/in	6.13 N/cm	TPU	30 oz/in	3.28 N/cm

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryplastics.com Nijverheidsstraat 10 2260 Oevel (Westerlo) Belgium 32-014-722500 Fax 32-014-722570 6/7/12