POLYKEN®

833

Multi-Purpose PE Tape



Backing: Polyethylene Film

Adhesive: Modified Rubber

Liner: N/A

Colors: Clear, Red, White, Yellow, Silver, Black, Pink, Green, Blue

Specifications: N/A

Standard Sizes: 48mm x 55m, 72mm x 55m

Applications

- General purpose abatement applications such as hanging and patching PE sheeting, securing waste disposal bags, and more
- Labeling & color coding
- Bundling, wrapping, and repairs
- Wire hold down (AV Cord Tape)
- Multiple uses in the convention industry - such as bundling, color coding, and splicing
- Polyethylene splicing
- Surface protection
- Dissimilar metal tape

Features	Benefits
• Polyethylene Film Backing	• Conformable and flexible • Excellent durability & solvent resistance • Hand tearable with excellent adhesion
• Rubber based adhesive	• High tack for a secure bond • Repositionable & clean removal from many surfaces
• Low VOC	• Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED®

Physical Properties

	Standard UOM	Metric UOM	Test Method
Total Thickness (Clear)	7.5 mils	0.191 mm	ASTM D-1000
Total Thickness (Colors)	7.0 mils	0.178 mm	ASTM D-1000
Adhesion to Steel	75 oz/in	8.21 N/cm	PSTC-101
Adhesion to Backing	40 oz/in	4.38 N/cm	PSTC-101
Tensile Strength	25 lb/in	43.78 N/cm	ASTM D-1000
Application Temperature	30 to 160° F	-1 to 71° C	
Operating Temperature	20 to 200° F	-6.7 to 93° C	
Elongation	85%		

Recommended Storage Conditions: 40-60% Humidity, 60ºF-80ºF
Standard Shelf Life (at 25C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.

BERRY PLASTICS CORPORATION AND SUBSIDIARIES
LEADERSHIP BY DESIGN

25 Forge Pkwy Franklin, MA 02038
1-800-343-7875 Fax 1-800-328-4822
www.berryplastics.com

Nijverheidsstraat 10
2260 Oevel (Westerlo) Belgium
32-014-722500 Fax 32-014-722570
3/24/14