


823 Polyethylene Electrical Tape



| Backing: | Polyethylene Film | | |
|---------------|---|--|--|
| Adhesive: | Rubber | | |
| Liner: | N/A | | |
| Colors: | Black | | |
| Specification | s: Meets UL 510 Requirements Meets DPM 881 | | |

Standard Sizes:

Applications

- Electrical & maintenance applications
- Wrapping and waterproofing wire harnesses
- For use when PVC electrical tapes are not suitable or permitted

| Features | Benefits |
|---|---|
| Polyethylene Film Backing | Conformable and flexible |
| | Excellent durability & solvent resistance |
| | Provides excellent dielectric strength |
| | Good performance indoors & out |
| Natural rubber based adhesive | Strong adhesive for a secure watertight seal |
| | • Suitable for use up ot 11,500V |

• Superior all-temperature performance

1"x36Yd, 48mm x 33m

• Excellent replacement for the combination for

the combination of splicing and friction tape

| Physical Properties | | | | | |
|-------------------------|--------------|-------------|-------------|--|--|
| | Standard UOM | Metric UOM | Test Method | | |
| Total Thickness | 9.5 mils | 241.3 mic | ASTM D-1000 | | |
| Adhesion to Steel | 31 oz/in | 3.39 N/cm | PSTC-101 | | |
| Adhesion to Backing | 20 oz/in | 2.19 N/cm | PSTC-101 | | |
| Tensile Strength | 17 lb/in | 29.77 N/cm | ASTM D-1000 | | |
| Application Temperature | -10 - 180°F | -23 - 82 °C | | | |
| Operating Temperature | -40 - 180°F | -40 - 82 °C | | | |
| Elongation | 220% | | | | |

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F Standard Shelf Life (at 25C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryplastics.com Nijverheidsstraat 10 2260 Oevel (Westerlo) Belgium 32-014-722500 Fax 32-014-722570 2/21/2012