




## Extreme Weather Foil Tape



- Backing:** 1.75mil Aluminum Foil
- Adhesive:** Acrylic
- Liner:** Unbleached Natural Kraft Paper
- Colors:** Aluminum

- Specifications:** UL 723 Listed & Meets FAR 25.853(a)
- Standard Sizes:** 48mm x 46M, 72mm x 46M

### Applications

- Taping joints and seams in duct work for A/C, heating, and ventilation systems
- Insulation seaming and patching
- Sealing insulation and repairing in cooler/refrigeration applications
- General purpose industrial and automotive uses
- Aircraft sealing & masking
- Window mask to protect aircraft canopies, windshields and passenger window surfaces from crazing or hazing during paint stripping

### Features

- 1.75 mil Aluminum Foil Backing
- High Performance Acrylic Adhesive
- UL 723 Listed. Meets FAR 25.853(a).
- Low VOC Content

### Benefits

- Conformable to fit corners and joints
- UV, moisture and mold resistant
- Non-solvent for less odor and low VOC content
- High tack, aggressive bond to surfaces
- Excellent performance in extreme cold or heat
- Meets flammability requirements for use in construction, aerospace and marine applications
- Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED®

### Physical Properties

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	3.5 mils	88.9 mic	ASTM D-1000
<b>Foil Thickness</b>	1.8 mils	45.72 mic	ASTM D-1000
<b>Adhesion to Steel</b>	55 oz/in	6.02 N/cm	PSTC-101
<b>Tensile Strength</b>	14 lb/in	24.52 N/cm	ASTM D-1000
<b>Operating Temperature</b>	-35 - 260° F	-37 - 126° C	
<b>Minimum Application Temp</b>	-25° F	-32° C	
<b>Smoke Developed</b>	0		
<b>Flame Spread</b>	0		
<b>VOC Content</b>	<30 g/L		

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F  
 Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.