Huntsman Advanced Materials Americas Inc.
Customer Service Hotline: 800.367.8793 5121 San Fernando Road West Los Angeles, CA 90039 818.247.6210

Customer Service Faxline: 517.351.6255 Technical Inquiries: 800.817.8260



website: www.araldite.com e-mail: adhesives_group@huntsman.com

Product Data

Preliminary Data Sheet

EPOCAST[®] 54-A/B EPOXY LAMINATING SYSTEM

- High Strength
- Self Extinguishing
- Short Work Life

DESCRIPTION

Epocast 54-A/B epoxy laminating system is an unfilled, solvent-free, easy-to-handle product. It is self extinguishing and well suited for the manufacture and repair of composite structures. In addition to laminating applications, the Epocast 54-A/B epoxy system can be used for filament winding.

TYPICAL PROPERTIES AS RECEIVED

Property	54-A	54-B	54-A/B	Test Method
	Resin	Hardener	System	
Color	Light Yellow	Straw	Amber	Visual
Density, g/cc.	1.19	1.05		ASTM-D-792
Viscosity, cP @ 77°F (25°C)	9,000	400		ASTM-D-2196
Gel time, 100 gms at 77°F (25°C), min.			15-25	ASTM-D-2471
Shelf life at 77°F (25°C),				
unopened, months	12	12		

MIX RATIO

To 100 parts by weight of Epocast 54-A resin, add 15 parts by weight of Hardener 54-B. Mix both components thoroughly for several minutes to insure a complete and uniform mixture. Mix only that quantity which can be applied within several minutes after mixing to avoid excessive exotherm.

CURE SCHEDULE:

Five days at 77°F (25°C) or two hours at 150-200°F (66-93°C) after room temperature gel. The system can be handled and machined after 24 hours at room temperature.

TYPICAL CURED PROPERTIES (Not for specification purposes)

Test	Results	Test Method
Compressive Strength, 12-ply 7781 glass cloth,		
at 77°F (25°C), psi (MPa)	49,010 (338)	ASTM D695
Compressive Modulus, 12-ply 7781 glass cloth,		
at 77°F (25°C), Ksi (MPa)	3,399 (23,442)	ASTM D695
Flammability, 2-ply 7781 glass cloth, 60 sec., vertical		
Self Extinguish Time, sec.	0	FAR 25.853A
Drip Extinguish Time, sec.	0	
Burn Length, in. (cm)	3.5 (8.89)	

CAUTION:

Huntsman Advanced Materials Americas Inc. maintains up—to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement <u>prior to</u> using this material. Copies of the latest MSDS may be requested by calling our customer service group at 800-367-8793 or emailing your request to adhesives group@huntsman.com.

FIRST AID!

<u>Eyes and skin:</u> Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse. Inhalation: Remove subject to fresh air.

<u>Swallowing:</u> Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

IMPORTANT LEGAL NOTICE:

Sales of a referenced product ("Product") are subject to the general terms and conditions of sale of Huntsman Advanced Materials Americas Inc. ("Huntsman").

<u>WARRANTY</u>: Huntsman warrants to the Buyer that the Product will conform to the published specifications for that Product at the time of manufacture.

DISCLAIMER AND LIMITATION OF LIABILITY: EXCEPT AS SET FORTH ABOVE, SELLER MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Huntsman cannot control Buyer's application and use of the Product and accepts no responsibility therefore. No statement or recommendation contained in any Product literature may be construed as a representation about the suitability of a Product for the particular application of Buyer or user or as an inducement to infringe any relevant patent. Buyer is responsible to ensure that its intended use of the Product does not infringe any third-party's intellectual property rights. Huntsman neither assumes, nor authorizes any representative or other person to assume for it, any obligation or liability other than as is expressly set forth herein. UNDER NO CIRCUMSTANCES SHALL HUNTSMAN BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL, SPECIAL OR OTHER INDIRECT DAMAGES AS A RESULT OF A BREACH OF ANY WARRANTY OR THE FAILURE OF A PRODUCT OR ANY CLAIM THAT IS ESSENTIALLY BASED UPON SUCH BREACH OR FAILURE. Any claim by Buyer, whether arising in contract, tort, negligence, breach of warranty, strict liability, or otherwise, related to a Product shall be limited to, and the sole liability of Huntsman and the sole remedy of Buyer for any claims shall be for, the purchase price of the Product in respect of which such claim is made. The foregoing DISCLAIMER AND LIMITATION OF LIABILITY supersedes Buyer's documents.

<u>WARNING</u>: Technical data and results are based upon tests under controlled laboratory conditions and must be confirmed by Buyer by testing for its intended conditions of use. The Product has not been tested for, and therefore is not recommended or suitable for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or likely, or for uses for which implantation within the human body is intended, and Huntsman assumes no liability for any such uses.

© 2004 Huntsman Advanced Materials Americas Inc. Epocast is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all, countries.