


## FoilMastic™ UL181 B-FX Foil Tape



- Backing:** Printed 2 mil Foil
- Adhesive:** Butyl Rubber Adhesive
- Liner:** Blue LDPE Film
- Colors:** Aluminum
- Specifications:** UL181B-FX Listed  
Tested by SMACNA R & T Institute
- Standard Sizes:** 48mm x 31M, 72mm x 31M

### Applications

- Indoor/Outdoor sealing of low, medium, and high pressure HVAC systems including sheet metal and flexible duct systems
- Seal cracks and seams in gutters, sheet metal roofing, trailers, and more

### Features & Benefits

- Aggressive butyl mastic adhesive
- Conformable foil backing
- UL181B-FX Listed
- Low VOC Content
- Provides instant water and air-tight seal
- Resistant to moisture and solvents
- Performs to SMACNA 0.5", 1", 2", 3", 4", 6" and 10" w.g. pressure classes and seal classes A, B, and C\*
- Easy to use in tight spaces. Conforms easily to round, square or odd-shaped objects
- Meets code requirements and can contribute toward requirements for EA Credit 1 (Optimize Energy Performance) under LEED®
- Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED®

### Physical Properties

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	17 mils	431.8 mic	ASTM D-1000
<b>Adhesion to Steel</b>	90 oz/in	9.85 N/cm	PSTC-101
<b>Adhesion to Backing</b>	40 oz/in	4.38 N/cm	PSTC-101
<b>Tensile Strength</b>	23 lb/in	40.28 N/cm	ASTM D-1000
<b>Operating Temperature</b>	40 to 200 °F	4 to 93 °C	
<b>Smoke Developed</b>	<50		UL 723
<b>Flame Spread</b>	<25		UL 723
<b>VOC Content</b>	<1 g/L		

\* Results verified by the SMACNA Research & Testing Institute  
 Recommended Storage Conditions: 40-60% Humidity, 60°F - 80°F  
 Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.