



DW496

Thermal Spray Tape

DeWAL® DW496 is a pressure sensitive tape produced by laminating multiple layers of glass fabric and aluminum foil coated with a high temperature silicone adhesive. The silicone adhesive will release cleanly.

Applications:

- Masking tape in grit blasting, plasma, and flame spraying
- Masking where single-ply tape will not provide sufficient protection

Industry(s):

- Plasma & Thermal Spray Masking

Features and Benefits

- High temperature resistance
- Abrasion resistance
- Double-ply construction

Basic Physical Properties	Typical Value	Units	Test Method
Adhesion to Steel	781 / 70	g/cm / oz/in	ASTM-D 1000
Color	White	N/A	N/A
Construction	Typical Value	Units	Test Method
Substrate	Foil & Glass Cloth	N/A	N/A
Adhesive System	Silicone	N/A	N/A
Overall Thickness	0.3585 / 0.0141	mm / in	ASTM-D374
Min Width	6.35 / 0.25	mm / in	N/A
Max Width	660.4 / 26	mm / in	N/A
Heat and Flame	Typical Value	Units	Test Method
Max Operating Temp.	260 / 500	°C / °F	N/A
Processing & Packaging	Typical Value	Units	Test Method
Shelf Life	18	Months from DOM	N/A
Shelf Life Storage Temp.	21 / 70	°C / °F	N/A
Roll Length	33 / 36	m / yd	N/A
Standard Core Type	Plastic	N/A	N/A
Core Diameter	76 / 3	mm / in	N/A
Standard Liner	Yellow Bubble	N/A	N/A
Specifications	CPMC74116, GE: C10 - 12		
Specification(s)	• Typical values shown are from testing at date of manufacture and should not be used for specification limits. • Additional technical information and product specifications are available upon request. • Shelf life is 18 months from the date of manufacture with storage conditions of 21°C (70°F) and 50% RH. • All metric conversions are approximate.		

Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page. It does not guarantee the product's usefulness in all applications.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers DeWAL products for each application. The Rogers logo, DeWAL logo and DeWAL are trademarks of Rogers Corporation or one of its subsidiaries.