

# Chemlok® Y-1540 Adhesive

## Technical Data Sheet

Chemlok® Y-1540 adhesive is a one-coat adhesive used to bond peroxide curing silicone, EPDM and fluoroelastomers to cold rolled and phosphatized steel.

### Features and Benefits:

**Environmentally Resistant** – resists temperatures of 260°C (500°F) when bonding silicone rubber; provides good resistance to hot motor oils.

**Easy to Apply** – low viscosity allows for easy application by brush or dip methods.

**Excellent Appearance** – provides good cosmetics; dries to a clear to slight red coating.

### Elastomers:

- Nitrile (NBR) - peroxide cure
- Hydrogenated Nitrile (HNBR) - peroxide cure
- Fluoroelastomer (FKM) - peroxide cure
- EPDM - peroxide cure
- Silicone (VMQ, PMQ, PVMQ) - peroxide cure
- EPDM/Silicone Blends

### Application:

**Surface Preparation** – Thoroughly clean metal surfaces prior to application. Remove protective oils, cutting oils and greases by solvent degreasing or alkaline cleaning. Remove rust, scale or oxide coatings by suitable chemical or mechanical cleaning methods.

For further detailed information on surface preparation of specific substrates, refer to Chemlok Adhesives application guide.

**Mixing** – No mixing is required before or during use. If dilution is needed, use methanol or ethanol at a ratio of 1:1, by volume.

**Applying** – Apply adhesive by dip or brush methods.

**Drying/Curing** – Allow adhesive to air-dry for at least 3 hours at 16-38°C (60-100°F) prior to bonding. Oven drying at temperatures up to 93°C (200°F) can also be used. Bond coated parts within 2-3 days after coating.

**Cleanup** – Use alcohol or ketones to clean up adhesive.

### Shelf Life/Storage:

Shelf life is six months from date of shipment when stored by the recipient at 10-32°C (50-90°F) in original, unopened container.

### Typical Properties\*

Appearance	Red Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 2, 60 rpm	~3
Density kg/m <sup>3</sup> (lb/gal)	838.8 - 862.8 (7.0 - 7.2)
Solids Content by Weight, %	8 - 12
Flash Point (Seta), °C (°F)	9.4 (49)
Solvents	Methanol

\*Data is typical and not to be used for specification purposes.

## Cautionary Information:

Before using this or any Parker Lord product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this document represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as Parker Lord has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Parker Lord does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

**WARNING — USER RESPONSIBILITY. FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.**

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its subsidiaries or authorized distributors.

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems.

©2024 Parker Hannifin - All Rights Reserved

Information and specifications subject to change without notice and without liability therefor. Trademarks used herein are the property of their respective owners.

OD DS3257 08/24 Rev.5



Parker Lord  
**Engineered Materials Group**

111 LORD Drive  
Cary, NC 27511-7923  
USA

**phone +1 877 275 5673**

[www.Parker.com/EPM](http://www.Parker.com/EPM)