

# Chemlok® 8560D-1 Adhesive

OBSOLETE

## Technical Data Sheet

Chemlok® 8560D-1 adhesive is a general purpose, one-coat water-based adhesive that bonds a wide variety of vulcanized and unvulcanized rubber compounds to metal. It is suitable for dip applications and may be diluted for spraying.

When environmental conditions are severe, Chemlok 8560D-1 adhesive is recommended to be used over Chemlok 8007 Blue water-based primer.

## Features and Benefits:

**Versatile** – serves as a post vulcanization (cured rubber) bonding agent capable of bonding a wide variety of vulcanized rubber compounds.

**Convenient** – requires only a single coat for most applications, reducing labor, inventory and shipping costs.

**Environmentally Preferred** – uses water for dilution; has low VOC emissions.

## Elastomers:

- Natural Rubber (NR)
- Polyisoprene (IR)
- Styrene-butadiene (SBR)
- Polybutadiene (BR)
- Polyacrylate (ACM)
- Polyepichlorohydrin (ECO)
- Chlorinated Polyethylene (CPE)
- Chlorosulfonated Polyethylene (CSM)
- Polychloroprene (CR)
- Nitrile (NBR)
- Butyl (IIR)
- EPDM Polymers
- Ethylene Acrylic (AEM)

## Application:

**Surface Preparation** – Thoroughly clean metal surfaces prior to application. Remove protective oils, cutting oils and greases by solvent degreasing or alkaline cleaning. Remove rust, scale or oxide coatings by suitable chemical or mechanical cleaning methods.

For further detailed information on surface preparation of specific substrates, refer to Chemlok Adhesives application guide.

**Mixing** – Thoroughly mix adhesive before use. Do not shake. To prevent foaming, mechanical mixing should not exceed 30 rpm. The addition of anti-foaming agents is not recommended.

If dilution is needed, use deionized water.

**Applying** – Apply adhesive by spray or dip methods. For best results, preheating the metal parts to 49-60°C (120-140°F) prior to adhesive application is recommended.

Regardless of application method, the dry film thickness of Chemlok 8560D-1 adhesive should be 12.7-25.4 micron (0.5-1.0 mil). Where minimum environmental resistance is required, film thickness in the lower range can be used on easy-to-bond rubber compounds. Thicker films within this range may be necessary on certain hard-to-bond rubber compounds where maximum environmental resistance is required or for post vulcanization bonding.

## Typical Properties\*

Appearance	Black/Green Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 2, 30 rpm	100 - 500
Density kg/m <sup>3</sup> (lb/gal)	1186.3 - 1234.2 (9.9 - 10.3)
Solids Content by Weight, %	43 - 47
Flash Point (Seta), °C (°F)	>93 (>200)
Solvents	Deionized Water

\*Data is typical and not to be used for specification purposes.



ENGINEERING YOUR SUCCESS.

**Drying** – Allow applied adhesive to air-dry for 30-60 minutes at room temperature. Oven drying at 49-71°C (120-160°F) in a recirculating forced air oven is recommended. Allow longer dry times during humid conditions.

## Shelf Life/Storage:

Shelf life is three months from date of shipment when stored by the recipient at 21-27°C (70-80°F) in original, unopened container. Do not freeze product.

## Cautionary Information:

Before using this or any Parker LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this document represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as Parker LORD has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Parker LORD does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

**WARNING — USER RESPONSIBILITY. FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.**

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its subsidiaries or authorized distributors.

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems.

©2022 Parker Hannifin - All Rights Reserved

Information and specifications subject to change without notice and without liability therefor. Trademarks used herein are the property of their respective owners.

OD DS4541 07/22 Rev.0



Parker LORD  
**Engineered Materials Group**

111 LORD Drive  
Cary, NC 27511-7923  
USA

**phone +1 877 ASK LORD (275 5673)**

[www.lord.com](http://www.lord.com)