

Cor-Ban®

CORROSION INHIBITING COMPOUNDS

COR-BAN® 22



Product description:
**CORROSION INHIBITING
COMPOUND**

FEATURES:

- ▶ A long lasting, water displacing, corrosion inhibiting compound
- ▶ **Cor-Ban® 22** formula is based on the **Cor-Ban® 27L** CIC
- ▶ A soft and self healing finished coating

KEY BENEFITS:

- ▶ No cracking or flaking to -60°F (-51°C)
- ▶ **Cor-Ban® 22** can be applied to corroded areas to prevent further corrosion from occurring
- ▶ Provides additional barrier protection for corrosion prone internal steel bores of horizontal pivot shafts and landing gear bogies
- ▶ Film is detectable and non-sagging
- ▶ Solvent removable
- ▶ A military approved CIC for stopping corrosion on pre-corroded metal parts
- ▶ Highly penetrating formula delivers the corrosion protection of **Cor-Ban® 27L** into faying surfaces



Rev: 20062E
10-20-2021

 For more information contact us :
zipchem@addevmaterials.com

 Part of 

COR-BAN® 22



Product description: CORROSION INHIBITING COMPOUND

KEY BENEFITS:

- ▶ Preferred CIC for routine maintenance
- ▶ > 4000 hours of salt spray

SPECS:

- Boeing BMS 3-23 (Meets requirements)
- NSN 8030-01-523-4290 (16 fl oz (473 ml) Aerosol)
- NSN 8030-01-531-7352 (5 Gallon (18.9L) Pail)
- T.O. 1C-130A-23 (Called out)
- T.O. 1C-5A-23 (Called out)

APPLICATIONS:

- ✓ Apply by conventional airless, air-operated spray equipment, or by aerosol
- ✓ **Cor-Ban® 22** can be applied over pre-existing corrosion
- ✓ The coating can be applied as thin as 1 mil (25 microns) film thickness to achieve the desired corrosion protection
- ✓ The **Cor-Ban® 22** aerosol can be used in conjunction with the **Formit®** extensions to provide targeted spray to areas that may be difficult to reach but need to be coated. Please refer to the **Formit®** technical data sheet for more information.
- ✓ All properties represented were achieved with a wet film thickness of 1.0 mils (25 microns). This wet film thickness can be measured with **Zip-Chem®**'s **Wet Film Thickness Gauge**.
- ✓ One aerosol can covers approximately 90 ft² (8.3 m²)
- ✓ Paste application of **Cor-Ban® 22** is available as **Cor-Ban® 27L**

COR-BAN® 22



Product description:
**CORROSION INHIBITING
COMPOUND**

PHYSICAL PROPERTIES:

- ▶ **Color:** reddish-brown
- ▶ **Compatibility Cd, Mg, Al:** Pass
- ▶ **Corrosion Resistance ASTM B-117:** >4000 hours on Steel
- ▶ **Flash Point:** 105°F (40°C)
- ▶ **Fungal Growth per Fed-STD-810 Method 508.7:** 0 (No Microbial Growth)
- ▶ **Low Temp Flaking:** Pass
- ▶ **Material VOC:** 538 g/L (4.4 Lbs/Gal)
- ▶ **Non-Volatiles:** 33%
- ▶ **Penetration:** BMS 3-23F pass
- ▶ **Solvent Type:** Aliphatic
- ▶ **Specific Gravity:** 0.82
- ▶ **Water Displacement:** 0% Rust
- ▶ **Water Resistance:** Pass



Cor-Ban[®]

CORROSION INHIBITING COMPOUNDS

COR-BAN[®] 22



Product description:

CORROSION INHIBITING COMPOUND

AVAILABLE PACK SIZES:

- ▶ Case of 12 of 16 fl oz (473 ml) Aerosol-007047
- ▶ Case of 24 of 4 fl oz (118 ml) Aerosol-103734
- ▶ Case of 4 Gallon (4 each of 3.8L) Cans -009400
- ▶ 5 Gallon (18.9L) Pail-007049
- ▶ 55 Gallon (208L) Drum-007050
- ▶ Special Packaging Upon Request



For more information contact us :
zipchem@addevmaterials.com



Part of



ADDEVMATERIALS