

# LOCTITE EA 9360 AERO

## Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9360)

### INTRODUCTION

LOCTITE EA 9360 AERO is a two-component toughened paste adhesive, which combines high peel strength at room temperature with tensile lap shear strength @ 225°F to 250°F (107°C to 121°C).

### FEATURES

- Available in dual cartridge packaging
- High peel strength
- Excellent static stress durability
- >225°F (107°C) service
- Easy mixing two component system
- Room temperature cure
- Low Slump

### Uncured Properties

	<u>Part A</u>	<u>Part B</u>	<u>Mixed</u>
Color	Off White	Blue	
Viscosity @ 77°F Brookfield, HBT	3000 Poise Spdl 7 @ 20 rpm	1700 Poise Spdl 6 @ 20 rpm	1200 Poise Spdl 5 @ 20 rpm
Viscosity @ 25°C Brookfield, HBT	300 Pa·S 2.1 rad/sec	170 Pa·S 2.1 rad/sec	120 Pa·S 2.1 rad/sec
Density (g/ml)	1.16	1.00	1.14
Shelf Life			
@ <40°F/4°C	1 year	1 year	
@ <77°F/25°C	6 months	6 months	
@ <90°F/32°C	6 months	6 months	

This material will normally be shipped at ambient conditions, which will not alter our standard warranty, provided that the material is placed into its intended storage upon receipt. Premium shipment is available upon request.

### Handling

**Mixing** - This product requires mixing two components together just prior to application to the parts to be bonded. Complete mixing is necessary. The temperature of the separate components prior to mixing is not critical, but should be close to room temperature 77°F (25°C).

<u>Mix Ratio</u>	<u>Part A</u>	<u>Part B</u>
By Weight	100	43
By Volume	2	1

# LOCTITE EA 9360 AERO

## Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9360)

**Note:** Volume measurement is not recommended for structural applications unless special precautions are taken to assure proper ratios.

**Pot Life** (200 gram mass) 50 minutes @ 77°F (25°C)  
Method - ASTM D2471 in water bath.

### Application

**Mixing** - Combine Part A and Part B in the correct ratio and mix thoroughly. THIS IS IMPORTANT! Heat buildup during or after mixing is normal. Do not mix quantities greater than 450 grams as dangerous heat buildup can occur causing uncontrolled decomposition of the mixed adhesive. TOXIC FUMES CAN OCCUR, RESULTING IN PERSONAL INJURY. Mixing smaller quantities will minimize the heat buildup.

**Applying** - Bonding surfaces should be clean, dry and properly prepared. For optimum surface preparation consult the LOCTITE Surface Preparation Guide. The bonded parts should be held in contact until the adhesive is set. Handling strength for this adhesive will occur in 24 hours at 77°F (25°C), after which the support tooling or pressure used during cure may be removed. Since full bond strength has not yet been attained, load application should be small at this time.

**Curing** - This adhesive may be cured for 5-7 days @ 77°F (25°C) to achieve normal performance. Accelerated cures up to 200°F (93°C) (for small masses only) may be used as an alternative. For example, 1 hour @ 180°F (82°C) will give complete cure.

**Cleanup** - It is important to remove excess adhesive from the work area and application equipment before it hardens. Denatured alcohol and many common industrial solvents are suitable for removing uncured adhesive. Consult your supplier's information pertaining to the safe and proper use of solvents.

### Bond Strength Performance

**Tensile Lap Shear Strength** - tested per ASTM D1002. Adherends are 2024-T3 Bare aluminum treated with phosphoric acid anodize per ASTM D3933.

Test Temperature, °F/°C	Typical Results	
	psi	MPa
-67 (-55)	4000	27.6
77 (25)	5000	34.5
180 (82)	3000	20.7
225 (107)	2000	13.8
250 (121)	950	6.5

# LOCTITE EA 9360 AERO

## Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9360)

**Tensile Lap Shear Strength** - tested per ASTM D1002. Adherends are 2024-T3 AlClad aluminum treated with phosphoric acid anodize per ASTM D3933.

### Process Variables (Various Adhesive Cure Schedules)

Adhesive Cure Parameter	Test Temp.		Typical Results	
	°F	°C	psi	MPa
Control: 7 days at 77°F (25°C)	75	24	5904	40.7
	212	100	3133	21.6
72 hrs at 77°F (25°C)	75	24	4724	32.6
1 hr at 146°F (65°C)	75	24	5917	40.8
	212	100	3412	23.5
45 minutes at 194°F (90°C)	75	24	5915	40.8
	212	100	3314	22.9

**Tensile Lap Shear Strength** - tested per ASTM D1002. Adherends are 2024-T3 AlClad aluminum treated with phosphoric acid anodize per ASTM D3933 and primed with BR-127.

### Dry, Heat Aging, Hot/Wet, Aircraft Fluids

Specimen Conditioning	Test Temp.		Typical Results	
	°F	°C	psi	MPa
Dry	-67	-55	4618	31.8
	75	24	5904	40.7
	212	100	3133	21.6
Heat Aging 168 hrs at 250°F (121°C)	-67	-55	5140	35.4
	75	24	5912	40.8
	212	100	4449	30.7
Hot/Wet 1000 hrs at 158°F (70°C) & 85% RH	75	24	5712	39.2
	212	100	1845	12.7
DI Water 168 hrs at 158°F (70°C)	75	24	5705	39.3
	212	100	2019	13.9
Hydraulic Fluid (MIL-H-5606) 300 hrs at 158°F (70°C)	75	24	5791	39.9
	212	100	3618	25.0
Jet Fuel (JP8) 1000 hrs at 104°F (40°C)	75	24	6293	43.4
	212	100	2953	20.4
De-icing Fluid (IPA) 168 hrs at 75°F (24°C)	75	24	5987	41.5
	212	100	2191	15.1

# LOCTITE EA 9360 AERO

## Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9360)

### Peel Strength

**Floating Roller (Bell) Peel Strength** - tested per ASTM D3167. Adherends are 2024-T3 AlClad peeling skin 0.020 inch (0.51 mm) & backing skin 0.063 inch (1.6 mm) aluminum treated and with phosphoric acid anodize per ASTM D3933 and primed with BR-127.

Adhesive Cure Parameter	Typical Results Tested at 77°F (25°C)	
	lb/in	N/25mm
72 hours cure at 77°F (25°C)	60	265
7 days at 77°F (25°C)	68	303
7 days at 77°F (25°C) + post cure 168 hours at 248°F (120°C)	35	156
1 hour cure at 149°F (65°C)	55	244
45 min. cure at 194°F (90°C)	30	135

**T-Peel Strength** - tested per ASTM D1876. Adherends are 2024-T3 Bare 0.020 inch (0.51 mm) thick aluminum treated with phosphoric acid anodize per ASTM D3933.

Adhesive Cure Parameter	Typical Results Tested at 77°F (25°C)	
	lb/in	N/25mm
5 days at 77°F (25°C)	49	218
60 min. at 160°F (71°C)	30	134

### Service Temperature

Service temperature is defined as that temperature at which this adhesive still retains 1000 psi (6.9 MPa) using test method ASTM D1002 and is >225°F (107°C).

### Bulk Resin Properties

**Tensile Properties** - tested using 0.125 inch (3.18 mm) castings per ASTM D638.

Adhesive Cure 5 days at 77°F (25°C) & Tested at 77°F (25°C)		
Tensile Strength	6,145 psi	42.4 MPa
Young's Modulus	487.2 ksi	3360 MPa
Elongation at Break	5%	

**Thermal Conductivity** - Tested per ASTM E1461

Specific Heat, J/g	1.26
Conductivity, W/mK	0.25

# LOCTITE EA 9360 AERO

## Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9360)

**Thermal Property****Glass Transition Temperature (T<sub>g</sub>) - Storage Modulus (E')**

Rheometric Scientific DMTA IV, single cantilever, heat-up rate 5°C/min., frequency 1 Hz, strain 0.1%  
 Specimen Dimensions 1 inch (25.4 mm) x 0.49 inch (12.4 mm) x 0.063 inch (1.6 mm)

Adhesive Initial Cure Parameter	Adhesive Post Cure	°F	°C
7 days at 77°F (25°C)	None	151	66
7 days at 77°F (25°C)	1 hr. at 170°F (77°C)	203	95
30 days at 77°F (25°C)	1 hr. at 170°F (77°C)	207	97
7 days at 77°F (25°C)	1 hr. at 190°F (88°C)	216	102
7 days at 77°F (25°C)	1.5 hrs. at 200°F (93°C)	225	107

**Compression Strength & Modulus at 2% Offset** - Tested per ASTM D695 cylindrical samples 1.42 inch (36 mm) tall x 0.56 inch (14.2 mm) diameter. Adhesive cure 7 days at 77°F (25°C)

Specimen Conditioning	Test Temp.		Typical Results			
			Compression Strength		Compression Modulus	
			°F	°C	psi	MPa
Dry	-67	-55	20,377	141	391	2700
	75	24	9,878	68	368	2538
	212	100	914	6.3	49	338
Hot/Wet 1000 hrs at 158°F (70°C) & 85% RH	-67	-55	19,861	137	399	2752
	75	24	8,866	61	288	1986
	212	100	415	2.9	103	710

**Shore D Hardness on different cures**

Cure 1 : 1 hour @ 180°F  
 Cure 2 : 10 hours @ 150°F  
 Cure 3 : 7 days @ RT

**Shore D Hardness (ASTM 2240, Type D Durometer)**

	Cure 1*	Cure 2	Cure 3
Measurement 1	85	81	81
Measurement 2	80	83	83
Measurement 3	85	85	83
Average	83	83	82

\*specimen shows exotherm at the curing temperature

# LOCTITE EA 9360 AERO

## Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9360)

---

**Handling Precautions**

Do not handle or use until the Material Safety Data Sheet has been read and understood.  
For industrial use only.

**DISPOSAL INFORMATION**

Dispose of spent remover and paint residue per local, state and regional regulations. Refer to HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.

**PRECAUTIONARY INFORMATION****General:**

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling. Empty containers retain product residue and vapors so obey all precautions when handling empty containers.

**PART A**

**CAUTION!** This material may cause eye and skin irritation or allergic dermatitis. It contains epoxy resins.

**PART B**

**WARNING!** This material causes eye and skin irritation or allergic dermatitis. It contains amines.

Before using this product refer to container label and HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.



# LOCTITE EA 9360 AERO

## Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9360)

### Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Rev. 9/2013

Henkel Corporation Aerospace | 2850 Willow Pass Road | Bay Point, CA 94565  
PHONE: +1.925.458.8000 | FAX: +1.925.458.8030 | [www.henkel.com/aerospace](http://www.henkel.com/aerospace)

#### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

