

Chemlok® 6450-1 Adhesive

Technical Data Sheet

Chemlok® 6450-1 adhesive is a high-temperature adhesive used to bond NBR and HNBR compounds to metal. It can be applied as either a covercoat or one-coat adhesive.

When used as a two-coat system, bonds formed with Chemlok 6450-1 adhesive and Chemlok 207 primer are resistant to many adverse environmental conditions found in downhole applications, as well as display excellent tear strength.

Features and Benefits:

Versatile – bonds a variety of NBR and HNBR compounds to a variety of metal substrates when used in combination with Chemlok 207 primer; can be used as a one-coat adhesive.

Chemically Resistant – resists a variety of fluids, including oils and fuels, and various aqueous environments.

Environmentally Resistant – provides excellent resistance to water, humidity, salt spray and high temperatures.

Elastomers:

- Nitrile (NBR)
- Hydrogenated Nitrile (HNBR)

Application:

Surface Preparation – Thoroughly clean metal surfaces prior to application. Remove protective oils, cutting oils and greases by solvent degreasing or alkaline cleaning. Remove rust, scale or oxide coatings by suitable chemical or mechanical cleaning methods.

If applicable, allow primer to thoroughly dry before applying Chemlok 6450-1 adhesive.

For further detailed information on surface preparation of specific substrates, refer to Chemlok Adhesives application guide.

Mixing – Thoroughly stir adhesive before use, and agitate sufficiently during use to keep dispersed solids uniformly suspended. Dilution is not required; however if desired, MEK or xylene can be used as a diluent.

Applying – Apply adhesive by brush, spray or dip methods. For flow or pour application, Chemlok 6450-1P adhesive is recommended.

Regardless of application method, the dry film thickness of Chemlok 6450-1 adhesive should be 15.2-20.3 micron (0.6-0.8 mil).

Drying/Curing – Thoroughly dry coated parts prior to bonding assemblies. Chemlok 6450-1 adhesive cures during the rubber vulcanization process.

Cleanup – Use solvents such as xylene and MEK to remove adhesive before heat is applied. Once cured, removal by solvent is not possible.

Typical Properties*

Appearance	Green-Black Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 1, 60 rpm	0 - 100
Density kg/m ³ (lb/gal)	916.5 - 964.6 (7.65 - 8.05)
Solids Content by Weight, %	23 - 27
Flash Point (Seta), °C (°F)	0 (32)
Solvents	MEK, Xylene

*Data is typical and not to be used for specification purposes.

Shelf Life/Storage:

Shelf life is six months from date of shipment when stored by the recipient at 21-27°C (70-80°F) in original, unopened container.

Cautionary Information:

Before using this or any Parker Lord product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this document represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as Parker Lord has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Parker Lord does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

WARNING — USER RESPONSIBILITY. FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its subsidiaries or authorized distributors.

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems.

©2024 Parker Hannifin - All Rights Reserved

Information and specifications subject to change without notice and without liability therefor. Trademarks used herein are the property of their respective owners.

OD DS4539 04/24 Rev.1



Parker Lord
Engineered Materials Group

111 LORD Drive
Cary, NC 27511-7923
USA

phone +1 877 275 5673

www.Parker.com/EPM