

## Product Data

# EPIBOND® 1559 Products

## EPOXY ADHESIVES

- Self Extinguishing Adhesives
- Designed for Quick Repairs
- One to One Mix Ratio

### DESCRIPTION

Epibond 1559-A/B and Epibond 1559-C/D epoxy adhesives are two-part, self-extinguishing pastes. The adhesives exhibit extremely quick set times, even at colder temperatures, making them suitable for fast repairs and other bonding applications. Epibond 1559 epoxy adhesives bond well to metals, composite laminates, most thermoplastics and dissimilar materials. Handling strength is developed in as little as ten minutes with high strength in one hour. Parts A and B are supplied in contrasting colors so that complete mixing is indicated by a uniform gray color. Parts C and D are both off-white for aircraft interior applications. Epibond 1559 epoxy adhesives can be used to fabricate or repair aircraft interior parts, which fulfill the FAR 25.853 and O.S.U. requirements when used in conjunction with other low combustible composite components.

### TYPICAL PROPERTIES AS RECEIVED

<u>Property</u>	<u>1559-A Resin</u>	<u>1559-B Hardener</u>	<u>1559-A/B System</u>	<u>Test Method</u>
Color	Lt. Blue	Gray	Lt. Gray	Visual
Density, g/cc.	1.20	1.20	1.20	ASTM-D-792
Viscosity, cP @ 77°F (25°C)	90,000	80,000	80,000	ASTM-D-2196
Gel time, 50 gms at 77°F (25°C), minutes	--	--	6	ASTM-D-2471
Shelf life at 77°F (25°C), unopened, months	12	12	--	--

**NOTE:** Store material at or above 75°F (23°C). If crystallized, place containers in 120°F (49°C) oven for 15-30 minutes. Allow material to cool to room temperature before mixing.

### MIX RATIO

To one part by weight or volume of Epibond 1559-A or C resin, add one part by weight or volume of Epibond 1559-B or D hardener.

**CURE SCHEDULE:** Epibond 1559-A/B and Epibond 1559-C/D: 24 hours at 77°F (25°C) or 30 minutes at 158°F (70°C).

### TYPICAL CURED PROPERTIES (Not for specification purposes)

<u>Test</u>	Ambient Temperature		<u>Test Method</u>
	<u>77°F (25°C)</u>	<u>45°F* (7°C)</u>	
Tensile lap shear, AL/AL, at 77°F (25°C), psi (MPa) after 1 hour	900 (6.2)	--	ASTM-D-1002
after 2 hours	1,245 (8.6)	775 (5.3)	--
after 4 hours	1,668 (11.5)	960 (6.6)	--
after 8 hours	2,670 (18.4)	1,010 (6.9)	--
after 16 hours	2,500 (17.2)	1,230 (8.5)	--
after 24 hours	2,900 (20)	1,260 (8.7)	--
After 14 days at 77°F (25°C), 95% RH	600 (4.1)	--	--
After 24 hours at 77°F (25°C), test at 160°F (71°C) after 30 minute soak	300 (2)	--	--
Flammability, 60 seconds ignition, vertical			FAR 25.853
Self-extinguish time, seconds	2		
Burn length, inches	5		

## CAUTION:

Huntsman Advanced Materials Americas Inc. maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 800-367-8793 or emailing your request to [adhesives\\_group@huntsman.com](mailto:adhesives_group@huntsman.com).

## FIRST AID!

Eyes and skin: Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse.

Inhalation: Remove subject to fresh air.

Swallowing: Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

## KEEP OUT OF REACH OF CHILDREN

## FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

### IMPORTANT LEGAL NOTICE:

Sales of a referenced product ("Product") are subject to the general terms and conditions of sale of Huntsman Advanced Materials Americas Inc. ("Huntsman").

WARRANTY: Huntsman warrants to the Buyer that the Product will conform to the published specifications for that Product at the time of manufacture, and that the Product will be free from defects in material and workmanship in normal use.

DISCLAIMER AND LIMITATION OF LIABILITY: EXCEPT AS SET FORTH ABOVE, SELLER MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Huntsman cannot control Buyer's application and use of the Product and accepts no responsibility therefore. No statement or recommendation contained in any Product literature may be construed as a representation about the suitability of a Product for the particular application of Buyer or user or as an inducement to infringe any relevant patent. Buyer is responsible to ensure that its intended use of the Product does not infringe any third-party's intellectual property rights. Huntsman neither assumes, nor authorizes any representative or other person to assume for it, any obligation or liability other than as is expressly set forth herein. UNDER NO CIRCUMSTANCES SHALL HUNTSMAN BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL, SPECIAL OR OTHER INDIRECT DAMAGES AS A RESULT OF A BREACH OF ANY WARRANTY OR THE FAILURE OF A PRODUCT OR ANY CLAIM THAT IS ESSENTIALLY BASED UPON SUCH BREACH OR FAILURE. Any claim by Buyer, whether arising in contract, tort, negligence, breach of warranty, strict liability, or otherwise, related to a Product shall be limited to, and the sole liability of Huntsman and the sole remedy of Buyer for any claims shall be for, the purchase price of the Product in respect of which such claim is made. The foregoing DISCLAIMER AND LIMITATION OF LIABILITY supersedes Buyer's documents.

WARNING: Technical data and results are based upon tests under controlled laboratory conditions and must be confirmed by Buyer by testing for its intended conditions of use. The Product has not been tested for, and therefore is not recommended or suitable for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or likely, or for uses for which implantation within the human body is intended, and Huntsman assumes no liability for any such uses.

© 2004 Huntsman Advanced Materials Americas Inc.  
Epibond is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all, countries.