

# RC-3500HT

## Breather fabric

Ideally suited to thermoplastic and aerospace applications

### Features

- Non-woven fibreglass felt capable of operating at temperatures above 538°C (1000°F) without taking a heat set, and pressures over 200PSI (13.8 bar).
- Engineered for use on polyimide curing, thermoplastic consolidations and very high temperature vacuum bagging applications.
- Recommended for use in thermo-insulation blankets and reusable breather blanket constructions.

### Properties

Maximum use temperature	538°C	1000°F
Colour	White	
Fibre	Fibreglass	
Weight	610g/m <sup>2</sup>	18oz/yd <sup>2</sup>

NB: RC-3500HT has no release characteristics and should be separated from the laminate by a suitable porous release fabric or film when used in conjunction with uncured materials.

### Availability

Standard width	Up to 1.16m	Up to 46in
Standard length	Up to 45.4m	Up to 50yd

### Storage

No special storage conditions required.

### Health & safety

No skin irritation problems experienced.

Handling of these products must conform to individual company guidelines and health and safety regulations.

All statements, technical information and recommendations contained in this data sheet are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any subsequent contract. All products are sold subject to the Cytec's Standard Terms and conditions of Sale. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. It is the responsibility of those wishing to sell items made from or embodying the products to inform the user of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information contained herein is under constant review and liable to be modified from time to time.

© Copyright 2012 – Cytec Process Materials (Keighley) Ltd, Cytec Process Materials (CA) Inc, Cytec Process Materials (Toulouse) Sarl, Cytec Process Materials (Milan) Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.