



## General Purpose PVC Film Tape

| Backing                                  | Backing:               | PVC Film   |  |  |  |  |  |
|--|------------------------|--|--|--|--|--|--|
| Adhesive<br>Single Coated<br>Self Wound  | Adhesive:              | Rubber (R306)  |  |  |  |  |  |
|  | Liner:                 | N/A  |  |  |  |  |  |
|  | Colors:                | Black, Brown, Purple, Red, Orange, White,<br>Yellow, Blue, Green |  |  |  |  |  |
|  | Specifications:        | A-A-1689B, Type II (supercedes PPP-T-66E, Type 1,<br>Class 2)    |  |  |  |  |  |
|  | Size Options:          | Incremental sizes 1/4" - 48" x 108Ft                             |  |  |  |  |  |
| Applications                             |                        |  |  |  |  |  |  |
| Color coding and striping                | •                      | Harness wrapping   |  |  |  |  |  |
| • Identifying safety equipment and hazar | Duct and joint sealing |  |  |  |  |  |  |
| Aisle and floor marking                  | •                      | Decorative packaging   |  |  |  |  |  |
| Features                                 |                        | Benefits   |  |  |  |  |  |
| PVC Film Backing                         | •                      | Conformable to irregular surfaces                                |  |  |  |  |  |
|  | •                      | Excellent solvent, chemical, moisture, and                       |  |  |  |  |  |
|  |                        | abrasion resistance  |  |  |  |  |  |
|  | •                      | Excellent for spiral wrapping                                    |  |  |  |  |  |
| Rubber Based Adhesive                    | •                      | Smooth, controlled unwind  |  |  |  |  |  |
|  | •                      | Strong bond to smooth and irregular surfaces                     |  |  |  |  |  |
| Typical Test Values                      |                        |  |  |  |  |  |  |
| Stando                                   | ard UOM Me             | tric UOM Test Method   |  |  |  |  |  |

|                         | Standa | Standard UOM  |       | MOL   | Test Method |
|-------------------------|--------|---------------|-------|-------|-------------|
| Total Thickness         | 6.0    | mils          | 0.152 | mm    | PSTC-133    |
| Substrate Thickness     | 5.0    | mils          | 0.127 | mm    | PSTC-133    |
| Adhesion to Steel       | 18     | oz/in         | 1.97  | N/cm  | ASTM D-3330 |
| Tensile Strength        | 18     | lb/in         | 31.52 | N/cm  | ASTM D-3759 |
| Elongation              | 250%   |               |       |       |             |
| Application Temperature | -14 to | -14 to 140 °F |       | 0 °C  |             |
| Operating Temperature   | -20 to | -20 to 176 °F |       | 30 °C |             |

Recommended Storage Conditions: 40-60% Humidity, 60 - 80  $^\circ\mathrm{F}$ 

Standard Shelf Life (at 25 °C): 12 months from shipment date

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Global's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryglobal.com 10/8/17