


## 6033

## **High Temperature PET Splicing Tape**



Backing: PET Film

Adhesive: Silicone (S607)

Liner: N/A

Colors: Clear

Specifications: N/A

**Size Options:** Incremental widths 1/4" - 35" x 108ft

## **Applications**

- Flashbreaker tape for composites
- OEM autoclaving applications
- Carrier device for small batteries (for hearing aids, watches, etc.)
- Splicing of photographic films, low surface energy films, and paper
- Border and blockout tape for screen printing

Features Benefits

PET Film Backing	Thin, low profile backing
	<ul> <li>Good puncture and tear resistance</li> </ul>
	Rigid and strong
	<ul> <li>Invisible splices</li> </ul>
Silicone Adhesive	<ul> <li>Bonds aggressively</li> </ul>
	<ul> <li>Allows initial repositioning</li> </ul>
	<ul> <li>Clean removal - resists staining and ghosting</li> </ul>
	<ul> <li>Solvent resistant</li> </ul>

## **Typical Test Values**

	Standar	Standard UOM		ОМ	Test Method
Total Thickness	3.5	mils	0.089	mm	PSTC-133
Substrate Thickness	2.0	mils	0.051	mm	PSTC-133
Adhesion to Steel	28	oz/in	3.06	N/cm	ASTM D-3330
Tensile Strength	50	lb/in	87.56	N/cm	ASTM D-3759
Elongation	150%				
Application Temperature	40 to 1	40 to 120 °F		9°C	
Operating Temperature	-40 to 300 °F		-40 to 149 °C		

Recommended Storage Conditions: 40-60% Humidity, 60-80 °F Standard Shelf Life (at 25 °C): 12 months from shipment date

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY GLOBAL'S knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

